

# SMU S Q+ Pipe

## DESCRIPTION

The SMU S Q+ range offers complete solutions for wastewater and stormwater drainage in buildings. High performance cast iron pipes with zinc coating, designed for better resistance to external stress, recommended for almost all applications.

## RECOMMENDED USE


- Corrosive atmosphere
- Wastewater
- Rainwater

## STANDARDS & APPROVALS

- Industry Product Standards:
  - NF EN877
  - R 592 012-3:2015 and EN 1561
- Acoustic Performance:  $L_{sc} \leq 10$  dB(A) &  $LaA = 47$  dB(A) according to EN 14366 with 2L/s.
- Range fire classification: A1

## Coatings:

- 1 External coating:** red-brown, anti-corrosive acrylic primer paint, average dry film thickness of 40  $\mu$ m.
- 2 Anti-corrosive layer:** flame-applied zinc metal coating of 130g/m<sup>2</sup>.
- 3** Cast-iron made with the De Lavaud process.
- 4 Internal coating:** two-component ochre-coloured epoxy coating, average dry film thickness of 130  $\mu$ m.




## TECHNICAL FEATURES

- Hot water resistance: 24h at 95°C.
- Thermal cycle resistance: 1500 cycles between 15°C and 93°C.
- Chemical resistance for  $2 \leq pH \leq 12$ .
- Salt spray resistance: more than 1500 h.


## ENVIRONMENTAL DATA

- Percentage of Recycled Content: 99 %
  - Recycling Information: Cast iron is 100% recyclable through the existing recycling industrial network.
- Data source: Declaration of recycled content.



# SMU S Q+

## Pipe



DN	L	H	W	Weight	Product Code
50	3000	58	58	12.9	237013
75	3000	83	83	18.8	237014
100	3000	110	110	25.1	237016
125	3000	135	135	35.3	237017
150	3000	160	160	42.1	237019
200	3000	210	210	69.1	254489
250	3000	274	274	99.5	254490
300	3000	326	326	129.4	254501

All dimensions are in mm and nominal weights are in kg

This document is provided for information purposes only and our company reserves the right to modify the information contained herein at any time. Our company declines all responsibility in the event of the use or installation of materials that do not comply with the rules prescribed in this document as well as with the standards, the technical documents and the applicable professional standards. Any orders placed will be subject to our General Terms and Conditions of Sale, available on request. The drawings and/or images are the exclusive property of Saint-Gobain PAM and are confidential. They must not be reproduced or disclosed to any third party without written consent. They may only be used for the purpose for which they were issued and are returnable on request.

**Saint-Gobain PAM Bâtiment**