

# ITINERO

## Blank end



### DESCRIPTION

Part of the range dedicated to infrastructure, the ITINERO blank ends enable you to cap the ends of pipes or fittings. Designed for surface water from bridges and tunnels, the cast iron fittings are coated with a thick grey powder epoxy layer and are indefinitely recyclable.

### Material & Coatings

- Cast Iron
- Coating: mat grey RAL 7030, epoxy, average dry film thickness 300 µm.

### RECOMMENDED USE

- Aggressive outdoor environment
- Buried networks
- Hydrocarbon Wastewater
- Runoff water

### TECHNICAL FEATURES


- Hot water resistance: 24h at 95°C.
- Thermal cycle resistance: 1500 cycles between 15°C and 93°C.
- Chemical resistance for  $2 \leq \text{pH} \leq 12$ .
- Salt spray resistance: more than 4500 h.


### STANDARDS & APPROVALS

- Industry Product Standards:
  - NF EN877
- Acoustic Performance:  $L_{sc} \leq 10 \text{ dB(A)}$  &  $LaA = 47 \text{ dB(A)}$  according to EN 14366 with 2L/s.
- Range fire classification: A2-s1,d0

### ENVIRONMENTAL DATA

- Percentage of Recycled Content: 99 %
- Recycling Information: Cast iron is 100% recyclable through the existing recycling industrial network.  
Data source: Declaration of recycled content.





DN	L	H	W	Weight	Product Code
100	110	40	110	0.8	277819
125	135	45	135	1.2	277825
150	160	50	160	1.7	277901
200	210	60	210	3.2	277902
250	274	70	274	5.9	277903
300	326	80	326	10	277904
400	429	98	429	21	277895

All dimensions are in mm and nominal weights are in kg

This document is provided for information purposes only and our company reserves the right to modify the information contained herein at any time. Our company declines all responsibility in the event of the use or installation of materials that do not comply with the rules prescribed in this document as well as with the standards, the technical documents and the applicable professional standards. Any orders placed will be subject to our General Terms and Conditions of Sale, available on request. The drawings and/or images are the exclusive property of Saint-Gobain PAM and are confidential. They must not be reproduced or disclosed to any third party without written consent. They may only be used for the purpose for which they were issued and are returnable on request.

**Saint-Gobain PAM Bâtiment**